

PressoGraf-SB



| | | |
|--|---|--|
| Тип покрытия: | Caucho | |
| Возможное назначение: | Production and conversion of plastic film, PVC, flexible packaging, (card)board, tape, labels, adhesives and aluminium foil : rollers where solvent resistance and antistatic properties are required | |
| | Rollers for lamination, both solventless and solvent based - cold and hot lamination | |
| | Backing rollers for (hot melt) glue application, printing and coating | |
| | Cover quality adapted for composite sleeves | |
| Диапазон твердости: | 70, 75, 80, 85, 90 Shore A | |
| Доступные цвета: | черный | |
| Рекомендуемая толщина покрытия: | мин. 10 mm - макс. 25 mm | |
| Температурная стойкость: | сухие условия: | постоянно 110°C / пиковые значения 130°C |
| | влажные условия: | постоянно 80°C / пиковые значения 95°C |
| Характеристики и преимущества: | O Good and stable electrical conductivity (antistatic properties) | |
| | Excellent resistance against polar solvents, like MEC and ethyle acetate | |
| Специальные характеристики: | Антистатика | |
| Химическая стойкость: | Кислотные растворы: | Очень хорошо |
| | Щелочные растворы: | Очень хорошо |
| | Горячая вода и пар: | Очень хорошо |
| | Озон: | Отлично |
| | Смазочные материалы: | Не подходит |
| | Ароматические растворители (толуол, бензол, ...): | Не подходит |
| | Хлорированные растворы: | Не подходит |
| | Полярные растворители(МЕК, ацетон,...): | Отлично |
| | Спирты (этанол, IPA,...): | Отлично |
| | Сопrotивление старению: | Отлично |
| Рекомендуемые средства очистки: | Полярные растворители (МЭК, этилацетат, спирт...), детергенты - избегать углеводороды! | |